

Argentojarosite



©2001-2005 Mineral Data Publishing, version 1

Crystal Data: Hexagonal. *Point Group:* $\bar{3} 2/m$. Typically as scaly masses of minute {0001} crystals with hexagonal outlines, or in pulverulent crusts.

Physical Properties: *Cleavage:* On {0001}, distinct. *Fracture:* [Uneven to conchoidal.] (by analogy to jarosite). *Tenacity:* [Brittle.] *Hardness* = n.d. *D(meas.)* = 3.66 *D(calc.)* = 3.660

Optical Properties: Transparent to translucent. *Color:* Yellow to brown; yellow in transmitted light. *Luster:* Adamantine.

Optical Class: Uniaxial (-). *Pleochroism:* *O* = yellow; *E* = pale yellow. ω = 1.882–1.888 ϵ = 1.785–1.790

Cell Data: *Space Group:* $R\bar{3}m$. *a* = 7.347(10) *c* = 16.580(53) *Z* = 3

X-ray Powder Pattern: Synthetic.

3.062 (100), 5.98 (50), 3.681 (30), 2.524 (30), 2.218 (30), 1.979 (25), 3.127 (20)

Chemistry:

	(1)	(2)
SO ₃	28.15	28.11
Fe ₂ O ₃	43.07	42.06
PbO	0.61	
Ag ₂ O	18.00	20.34
K ₂ O	0.42	
H ₂ O	9.81	9.49
insol.	0.29	
Total	100.35	100.00

(1) Tintic Standard mine, Utah, USA. (2) AgFe₃(SO₄)₂(OH)₆.

Mineral Group: Alunite group.

Occurrence: An uncommon secondary mineral in the oxidized portions of silver- and sulfide-bearing mineral deposits.

Association: Anglesite, barite, quartz (Tintic Standard mine, Utah, USA).

Distribution: In the USA, an ore mineral in the Tintic Standard mine, near Dividend, East Tintic district, Utah Co., Utah; in the Philadelphia mine, Organ district, Doña Ana Co., New Mexico; from the Cactus Queen mine, Kern Co., California. At the Santa Ana mine, Caborca, Sonora, Mexico. In England, in the West Turf Pits mine, Grassington Moor, Yorkshire; from the Treore mine, St. Teath, and at Wheal Ludcott, St. Ives, Cornwall. From the Rio Tinto, Huelva and La Union mines, Murcia, Spain.

Name: As the silver, *argentum*, analog of *jarosite*.

Type Material: The Natural History Museum, London, England, 1957,357; National Museum of Natural History, Washington, D.C., USA, 104272–104274, 94707, R6309.

References: (1) Palache, C., H. Berman, and C. Frondel (1951) Dana's system of mineralogy, (7th edition), v. II, 565. (2) May, A., J.J. Sjöberg, and E.G. Baglin (1973) Synthetic argentojarosite: physical properties and thermal behavior. *Amer. Mineral.*, 58, 936–941.