

Crystal Data: Monoclinic. *Point Group:* 2/m. Typically as incrustations of prismatic crystals, to 3 mm. *Twinning:* Pseudo-hexagonal trillings are produced by twinning, which may be polysynthetic.

Physical Properties: Hardness = 4.5 D(meas.) = ~5.1 D(calc.) = 4.50 Decomposes in H₂O, leaving PbSO₄.

Optical Properties: Transparent. *Color:* Colorless, pale gray, may be stained green. *Luster:* Vitreous.

Optical Class: Biaxial (-). *Dispersion:* $r > v$, strong. $\alpha = 1.743(5)$ $\beta = 1.754(5)$ $\gamma = 1.764(5)$ 2V(meas.) = Very large.

Cell Data: *Space Group:* P2₁/m. $a = 19.62$ $b = 7.14$ $c = 9.81$ $\beta = 90^\circ$ $Z = 4$

X-ray Powder Pattern: Beatriz mine, Chile. (ICDD 25-706).
2.927 (100), 1.906 (56), 3.55 (55), 2.876 (45), 2.132 (35), 8.45 (31), 4.03 (31)

Chemistry:	(1)	(2)
SO ₃	16.70	29.76
FeO	0.33	
ZnO	0.29	
PbO		55.32
Pb	50.88	
Cu	2.51	
Na ₂ O	trace	11.52
Cl	10.18	4.39
insol.	1.84	
-O = Cl ₂		0.99
Total		100.00

(1) Beatriz mine, Chile; partial analysis of impure material; composition established by crystal-structure analysis of natural and synthetic material. (2) Na₃Pb₂(SO₄)₃Cl.

Occurrence: A rare secondary mineral in the oxidized zone of chlorine-rich lead deposits.

Association: Boleite, pseudoboleite, bindheimite, anglesite, galena (Beatriz mine, Chile); atacamite, boleite, osarizawaite-beaverite, paratacamite (Herminia mine, Chile).

Distribution: From the Beatriz, Herminia, Santa Ana, and San Rafael mines, Sierra Gorda district, southwest of Calama, Antofagasta, Chile. In the Auguste-Victoria mine, Marl-Hüls, Ruhr Valley, North Rhine-Westphalia, Germany.

Name: For Caracoles, a town near the Beatriz mine, Chile.

References: (1) Palache, C., H. Berman, and C. Frondel (1951) Dana's system of mineralogy, (7th edition), v. II, 546-547. (2) Schneider, W. (1969) Bestimmung einer Überstruktur am Caracolit. Neues Jahrb. Mineral., Monatsh., 58-64 (in German with English abs.).