

Crystal Data: Orthorhombic. *Point Group:* 2/m 2/m 2/m. In massive aggregates to 1 cm.

Physical Properties: *Cleavage:* None. *Fracture:* Uneven. *Tenacity:* Brittle.
Hardness = 6 D(meas.) = n.d. D(calc.) = 4.61 Metamict.

Optical Properties: Transparent. *Color:* Amber-yellow. *Streak:* White. *Luster:* Adamantine.
Optical Class: Biaxial (n.d.). $\alpha = 1.694(2)$ $\beta = \text{n.d.}$ $\gamma = 1.715(5)$ $2V(\text{meas.}) = \text{n.d.}$
 $2V(\text{calc.}) = \text{n.d.}$ *Pleochroism:* None. Anomalous blue interference colors.

Cell Data: *Space Group:* Cmcm. $a = 14.979(6)$ $b = 10.548(5)$ $c = 6.964(3)$ $Z = 4$

X-ray Powder Pattern: Souris Valley, Komono, Mie Prefecture, central Japan. (Heated to 810° C)
2.68 (100), 3.76 (85), 3.54 (83), 3.48 (82), 2.16 (78), 4.26 (68), 5.46 (58)

Chemistry:	(1)	(1)	
SiO_2	14.70	Dy_2O_3	4.70
P_2O_5	1.06	Ho_2O_3	0.65
TiO_2	5.32	Er_2O_3	1.73
Al_2O_3	2.84	Tm_2O_3	0.39
Fe_2O_3	0.06	Yb_2O_3	2.13
Y_2O_3	45.14	Lu_2O_3	0.77
Ce_2O_3	0.39	ThO_2	1.59
Pr_2O_3	0.10	UO_2	0.63
Nd_2O_3	1.62	F	9.28
Sm_2O_3	1.59	$-\text{O} = \text{F}_2$	3.91
Gd_2O_3	3.99	$\underline{\text{H}_2\text{O}}$	2.19
Tb_2O_3	0.73	Total	97.69

(1) Souris Valley, Komono, Mie Prefecture, central Japan; average of 7 electron microprobe analyses supplemented by IR spectroscopy, H_2O from structure analysis; corresponding to $(\text{Y}_{3.13}\text{Dy}_{0.20}\text{Gd}_{0.17}\text{Yb}_{0.08}\text{Nd}_{0.08}\text{Sm}_{0.07}\text{Er}_{0.07}\text{Th}_{0.05}\text{Tb}_{0.03}\text{Ho}_{0.03}\text{Lu}_{0.03}\text{Ce}_{0.02}\text{Tm}_{0.02}\text{U}_{0.02})_{\Sigma=4.00}(\text{Ti}_{0.52}\text{Al}_{0.44}\text{Fe}_{0.01})_{\Sigma=0.97}(\text{Si}_{1.92}\text{P}_{0.12})_{\Sigma=2.04}\text{O}_9[\text{F}_{3.83}(\text{OH})_{1.91}]_{\Sigma=5.74}$.

Occurrence: In a block of granitic pegmatite collected from a talus slope.

Association: Quartz, albite, K-feldspar, muscovite, allanite-(Ce), gadolinite-(Y), magnesiorowlandite-(Y).

Distribution: In the Souris Valley, Komono, Mie Prefecture, central Japan. Also reported from El'ozero, Kola Peninsula, Russia.

Name: For the prefecture in Japan that produced the first specimens.

Type Material: National Museum of Nature and Science, Tokyo, Japan (NSM-M43627).

References: (1) Matsubara, S., R. Miyawaki, K. Yokoyama, M. Shigeoka, K. Momma and S. Yamamoto (2015) Mieite-(Y), $\text{Y}_4(\text{Ti})(\text{SiO}_4)_2\text{O}[(\text{F},\text{OH})]_6$, a new mineral in a pegmatite at Souris Valley, Komono, Mie Prefecture, central Japan. Journal of Mineralogical and Petrological Sciences, 110, 135-144. (2) (2016) Amer. Mineral., 101, 748-750 (abs. ref. 1).