

**Crystal Data:** Isometric. *Point Group:* 4/m  $\bar{3}$  2/m. As octahedral crystals, to 0.1 mm.

**Physical Properties:** *Cleavage:* None. *Fracture:* Irregular. *Tenacity:* Brittle.  
Hardness = n.d. D(meas.) = n.d. D(calc.) = 5.393

**Optical Properties:** Transparent. *Color:* Reddish brown. *Streak:* Pale yellow.  
*Luster:* Vitreous to resinous.  
*Optical Class:* Isotropic. *n*(calc.) = 1.950

**Cell Data:** *Space Group:* Fd $\bar{3}$  m. *a* = 10.3042(7) Z = 8

**X-ray Powder Pattern:** Buca della Vena mine, Stazzema, Apuan Alps, Tuscany, Italy.  
1.824 (vs), 1.556 (vs), 2.977 (s), 3.105 (m), 2.576 (m), 1.984 (m), 1.489 (m)

Chemistry:	(1)	(2)
Sb <sub>2</sub> O <sub>5</sub>	[63.73]	74.26
Sb <sub>2</sub> O <sub>3</sub>	[10.93]	
TiO <sub>2</sub>	3.53	
SnO <sub>2</sub>	0.28	
V <sub>2</sub> O <sub>3</sub>	0.68	
Al <sub>2</sub> O <sub>3</sub>	0.28	
PbO	0.68	
FeO	5.52	
MnO	0.13	
CaO	13.68	25.74
Na <sub>2</sub> O	0.83	
F	1.20	
-O = F <sub>2</sub>	0.51	
Total	100.96	100.00

(1) Buca della Vena mine, Stazzema, Apuan Alps, Tuscany, Italy; average of 6 electron microprobe analyses, Sb<sub>2</sub>O<sub>5</sub>;Sb<sub>2</sub>O<sub>3</sub> calculated using crystal-chemical considerations; corresponding to (Ca<sub>1.07</sub>Fe<sup>2+</sup><sub>0.34</sub>Sb<sup>3+</sup><sub>0.33</sub>Na<sub>0.12</sub>Pb<sub>0.01</sub>Mn<sub>0.01</sub>)<sub>Σ=1.88</sub>(Sb<sup>5+</sup><sub>1.73</sub>Ti<sub>0.19</sub>V<sub>0.04</sub>Al<sub>0.02</sub>Sn<sub>0.01</sub>)<sub>Σ=1.99</sub>(O<sub>6.68</sub>F<sub>0.28</sub>)<sub>Σ=6.96</sub>.

(2) Ca<sub>2</sub>Sb<sub>2</sub>O<sub>6</sub>O.

**Mineral Group:** Pyrochlore supergroup, roméite group.

**Occurrence:** In calcite-barite veins cutting deformed metavolcanic-metasedimentary rocks.

**Association:** Calcite, cinnabar, derbylite, dolomite, hematite, ‘mica’, pyrite, sphalerite, ‘tourmaline’.

**Distribution:** At the Buca della Vena mine, Stazzema, Apuan Alps, Tuscany, Italy. Also from Långban, Värmland, Sweden.

**Name:** For a member of the *roméite group* with dominant oxygen (as OH) in the Y structural site and calcium in the A structural site.

**Type Material:** At the Natural History Museum, University of Pisa, Italy (19640).

**References:** (1) Biagioni, C., P. Orlandi, F. Nestola, and S. Bianchin (2013) Oxycalcioroméite, Ca<sub>2</sub>Sb<sub>2</sub>O<sub>6</sub>O, from Buca della Vena mine, Apuan Alps, Tuscany, Italy: a new member of the pyrochlore supergroup. *Mineral. Mag.*, 77(7), 3027-3037. (2) (2015) Amer. Mineral., 100, 2357-2360 (abs. ref. 1).